


18 oz. Coated Vinyl Fabric



Royal Blue



White



Yellow



Tan



Orange



Pink



Red



Burgundy



Lime Green



Green




Marine Blue




Royal Blue



Navy



Purple



Grey



Black




SPALDING

The colors represented in regards to this product may vary within industry standards from actual material. While reliable, these colors are intended only as an informational source for your benefit and do not constitute a warranty and/or guarantee. The Purchaser is still required to determine if the color of the actual material meets the individual needs of the Purchaser.

18 oz. Coated Vinyl Fabric

- › Our signature 18 oz. coated formula is a durable, multi-purpose athletic vinyl engineered with low lead levels well below 100 ppm, which guarantees it is safe for kids. This product is C.P.S.I.A. approved (6P) and has no detection of DnHP (7P), assuring the lowest phthalate levels in the market. Treated with DuraGUARD®, an EPA registered anti-microbial agent, this product is protected against mildew and fungus, and has fire retardant certification for NFPA-701, Cal 117, and ASTM E-84, while achieving Class A.

Helpful Product Specifications

	ENGLISH	METRIC	TESTING METHOD
Weight	18 oz./yd ²	610 g/m ²	FS 5040 / ASTM D3776
Widths	up to 61"	up to 155 cm	
Construction	18 x 17/1" by 1000 x 1300	7 x 7/cm by 1100 x 1430	
Grab Tensile	375 x 375 lbs./1"	1668 X 1668 N/2.5 cm	FS 5100 / ASTM D5034
Tongue Tear	100 x 100 lbs./1"	445 x 445 N/2.5 cm	FS 5134 / ASTM D2261
Adhesion	26 lbs./2"	116 N/5 cm	FS 5970 / ASTM D751
Lead	Less than 100 ppm		C.P.S.I.A - H.R. 4040
6P (Phthalates)	Less than .1% - DnBP/DBP, BBP, DEHP, DnOP, DINP, DIDP		C.P.S.I.A - H.R. 4040
7P (Phthalate)	Less than .1% - DnHP		
Treatments	Anti-mildew, UV, DuraGUARD®		
Fire Retardant	Pass		NFPA-701, Cal 117
	Class A		ASTM E-84
Finish	Matte		
Put-Up	75 yds	69 m	



200 American Avenue | Jefferson, IA 50129 | 1-800-435-3865 | Fax: 515-386-8737 | www.spaldingequipment.com

The following information in regards to the chemical and physical properties of this product is based upon reliable testing methods. While reliable, these statistics are intended only as an informational source for your benefit. These statistics are, however, provided only as a convenience and do not constitute a warranty and/or guarantee. The Purchaser is still required to determine if the product represented meets the individual needs of the Purchaser.